

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 018 357 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
12.07.2000 Bulletin 2000/28

(51) Int. Cl.<sup>7</sup>: **B01D 39/20**

(21) Application number: **99200036.4**

(22) Date of filing: **08.01.1999**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(72) Inventors:  
• **Loncke, Jan**  
**8550 Zwevegem (BE)**  
• **Vandamme, Johan**  
**9800 Deinze (BE)**


(71) Applicant: **N.V. BEKAERT S.A.**  
**8550 Zwevegem (BE)**

(74) Representative:  
**Messely, Marc, Ir. et al**  
**N.V. Bekaert S.A.,**  
**Bekaertstraat 2**  
**8550 Zwevegem (BE)**

(54) **Layered filtering structure**

(57) A layered filtering structure (10) comprises at least a first layer (12) and a second layer (13). Each layer comprises a web of metal fibers which has been sintered. The two layers (12, 13) are in contact with each other. The first layer, most close to the filter inlet side has a porosity below 55 %, and the second layer, closer to the filter outlet side has a porosity which is at

least 20 % greater than the porosity of the first layer. The first layer is compacted in a separate manufacturing step. The layered filtering structure combines the advantage of a small filter rating with a low pressure drop.



**Fig. 1**

**EP 1 018 357 A1**

**Description****Field of the invention.**

- 5 [0001] The present invention relates to a layered filtering structure which is adapted for micro-filtration purposes. The term "micro-filtration" refers to filtering structures which are able to retain particles with a maximum size of between 0.5  $\mu\text{m}$  and 10  $\mu\text{m}$ , in particular below 2  $\mu\text{m}$ .

**Background of the invention.**

- 10 [0002] Presently available filter material for applications such as micro-filtration and for in situ cleanable filtration media conveniently comprise ceramic membrane layers fixed to the surface of porous sintered metal powder or metal fiber substrates. The high pressure drop across these filter laminates, however, is a considerable drawback since the filtering process requires additional energy due to the high pressure and robust mechanical supports for the filter layers.
- 15 In addition, repeated backflushing is difficult and, after all, the ceramic layers are quite brittle, which adversely affects durability.

**Summary of the invention.**

- 20 [0003] It is an object of the present invention to avoid the drawbacks of the prior art.
- [0004] It is also an object of the present invention to provide a filtering structure adapted for microfiltration without causing high pressure drops across the structure.
- [0005] It is still another object of the present invention to provide a filtering structure which allows for repeated back-flushing.
- 25 [0006] According to a first aspect of the present invention, there is provided a layered filtering structure which comprises at least a first layer and a second layer. Each layer comprises a web of metal fibers which have been sintered. The two layers are in contact with each other. The first layer, at the upstream side, so most close to the filter inlet side, has a porosity below 55 %. The second layer, at the downstream side, so closer to the filter outlet side, has a porosity which is at least 20 % greater than the porosity of said first layer. Preferably the porosity of the second layer is greater
- 30 than 80 %.
- [0007] The first layer with the lower porosity determines the filter rating, i.e. the size of the particles the majority of which still pass the filter.
- [0008] The fibers in the first layer preferably have a diameter of less than 3  $\mu\text{m}$ , e.g. less than 2.5  $\mu\text{m}$ , e.g. 2  $\mu\text{m}$ .
- [0009] The first layer preferably has a weight ranging from 300  $\text{g/m}^2$  to 600  $\text{g/m}^2$  so that its thickness is limited to a
- 35 range of between 0.05 mm to 0.15 mm. Generally, the pressure drop over a filter is about proportional to its thickness. In this case, the limited thickness of the first layer limits the resultant pressure drop to an acceptable degree. The degree of pressure drop over the second layer is considerably lower than the pressure drop over the first layer due to the greater porosity of the second layer. So the total pressure drop over the whole filtering structure is about equal to the limited pressure drop over the first layer.
- 40 [0010] An incoming fluid is immediately able to expand in the second layer once it has passed the first layer.
- [0011] The diameter of the fibers in the second layer is preferably three times greater than the diameter of the fibers in the first layer.
- [0012] In order to obtain the difference in porosity between the first layer and the second layer, the first layer is sintered and compacted separately and in advance. Only thereafter, this sintered and compacted first layer is brought in
- 45 contact with the second layer and a second sintering operation takes place to sinter the fibers in the second layer and to bond the two layers together.
- [0013] The reason for the separate sintering and compacting step of the first layer can be explained as follows.
- [0014] Compacting two or more layers of metal fiber webs together leads to a degree of porosity in the layers which is about the same over the whole layered structure, and this is to a great extent independent of the fiber diameter in the
- 50 different layers. This is in contrast with other filter media such as filter powders or filter particles. By separately sintering and compacting the first layer in advance, it is avoided that the second layer is compacted to more or less the same degree of the first layer.
- [0015] In a preferable embodiment of the invention, the first layer has at least one even smooth surface in order to provide a good contact with the second layer.
- 55 [0016] A cold isostatic pressing operation is to be preferred for the compacting operation of the first layer, since this allows obtaining a homogeneous filter medium. Cold isostatic pressing, however, leads to a slightly rough surface and not to an even and smooth surface. Preference is here given to a cold isostatic pressing operation where the pressure is applied from one side and where the other side of the layer rests on an even and smooth support in order to obtain

an even and smooth surface.

[0017] Preferably a wire net is fixed as support to the first layer or to the second layer. Most preferably the filtering structure is sandwiched between a first wire net fixed at the first layer at the inlet side and a second wire net fixed at the second layer at the outlet side. The meshes of the first wire net are smaller than the meshes of the second wire net. The diameters of the wires of the first wire net are smaller than the diameters of the wires of the second wire net.

[0018] Next to the function of support the first wire net still has another function and advantage. This first wire net generates some turbulence in the incoming flow which improves the anti-fouling behavior.

[0019] According to a second aspect of the present invention, there is provided a method of manufacturing a layered filtering structure. The method comprises the following steps:

- (a) sintering a web of metal fibers to form a first layer;
- (b) compacting the first layer to a porosity below 55 %;
- (c) providing a web of metal fibers to form a second layer;
- (d) bringing the first compacted layer and the second layer in contact with each other to form a layered assembly;
- (e) sintering the layered assembly to form a coherent entity wherein the second layer has a porosity which is at least 20 % higher than the porosity of the first layer.

[0020] Preferably the compacting step is done by means of a cold isostatic pressing operation.

#### **Brief description of the drawings.**

[0021] The invention will now be described into more detail with reference to the accompanying drawing wherein

- FIGURE 1 shows an enlarged view of a cross-section of a layered filtering structure according to the invention.

#### **Description of a preferred embodiment of the invention.**

##### **First Example.**

[0022] Referring to FIGURE 1, a layered filtering structure 10 according to the invention comprises a first layer 12 of a sintered and compacted fiber web. The fibers in the first layer have a diameter of 2  $\mu\text{m}$ . The weight of the first layer is 450 g/m<sup>2</sup>. The thickness is about 0.10 mm.

[0023] The first layer 12 is via a smooth and even surface direct in contact with a second layer 13 of a sintered fiber web. The fibers in the second layer have a diameter of 8  $\mu\text{m}$ . The weight of the second layer is 225 g/m<sup>2</sup>.

[0024] A first wire net 14 is fixed to the first layer 12. This first wire net 14 has been rolled to a thickness of 0.17 mm and has 48 meshes per inch (1 inch = 25.4 mm). Its weight is 380 g/m<sup>2</sup>.

[0025] A second wire net 15 is fixed to the second layer 13. This second wire net 15 has a thickness of 0.45 mm and has 40 meshes per inch. Its weight is 1220 g/m<sup>2</sup>.

[0026] A filtering structure as shown in FIGURE 1 can be made in the following way.

[0027] Steel fibers with a diameter of 2  $\mu\text{m}$  are obtained by means of the technique of bundled drawing, such as described, e.g., in US-A-3,379,000. A first non-woven web is then produced by means of a random-feeder apparatus which is disclosed e.g. in GB1 190 844. The web is then sintered separately and compacted by means of a cold isostatic pressing operation carried out at a pressure higher than 2000 bar to obtain a porosity lower than 55 %, e.g. lower than 50 %, e.g. 46 %. This results in the first layer 12.

[0028] Steel fibers with a diameter of 8  $\mu\text{m}$  are obtained with the above-mentioned technique of bundled drawing and are used to provide a second non-woven web. This second non-woven web will form the second layer 13. The second non-woven web is put on the second wire net 15 and the first layer 12 is put with its even surface on the second non-woven web. A first wire net 14, which has been pre-rolled, is put on the first layer. The thus obtained layered assembly is sintered together under a light pressure to obtain the layered filtering structure 10.

[0029] The layered filtering structure according to the invention has been subjected to a conventional test for measuring the air permeability and to a bubble point pressure test. The results are given hereunder.

	First layer	Whole filter
Weight (g/m <sup>2</sup> )	450	2275
Thickness (mm)		1.02
Global porosity (%)		72.22
Texttest		
Average (liter / dm <sup>2</sup> )		3.00 ± 15%
Bubble point pressure test		
Average (Pa)	27000 ± 15%	24520 ± 15%
Filter rating (μm)	1.37 ± 15%	1.51 ± 15%

### Second Example.

[0030] The same tests have also been applied to another layered filtering structure according to the invention. The difference with the structure of the first example, is now that the first layer is compacted not in an isostatical way. The first layer is now compacted between two plates until a thickness of about 0.10 mm is obtained.

	First layer	Whole filter
Weight (g/m <sup>2</sup> )	450	2275
Thickness (mm)	0.11	1.02
Global porosity (%)	46.63	72.22
Texttest		
Average (liter / dm <sup>2</sup> )	3.72 ± 15%	5.72 ± 15%
Bubble point pressure test		
Average (Pa)	18750 ± 15%	17430 ± 15%
Filter rating (μm)	1.97 ± 15%	2.12 ± 15%

[0031] Other embodiments according to the invention may be envisaged. As a matter of example only, following layered filtering structures are given:


diameter of filaments in first layer with low porosity (μm)	diameter of filaments in second layer with high porosity (μm)
4	12
6.5	22
8	30

[0032] The material used for the filtering structure according to the invention may be conventional compositions such as stainless steel 316®, Hastelloy®, Inconel® or Nichrome®. The latter composition can be applied for gas filtra-

tion at a high temperature.

# Claims

- 5 1. A layered filtering structure (10) comprising at least a first layer (12) and a second layer (13) each layer comprising a web of metal fibers which has been sintered, said two layers (12, 13) being in contact with each other, wherein said first layer, most close to the filter inlet side has a porosity below 55 %, and wherein said second layer, closer to the filter outlet side has a porosity which is at least 20 % greater than the porosity of said first layer.
- 10 2. A structure according to claim 1, wherein said second layer has a porosity of at least 80 %.
3. A structure according to any one of the preceding claims, wherein said first layer comprises metal fibers with a diameter of less than 3  $\mu\text{m}$  and wherein said second layer comprises metal fibers with a diameter of at least three times the diameter of the fibers in the first layer.
- 15 4. A structure according to any one of the preceding claims, wherein said first layer has a weight ranging between 300  $\text{g/m}^2$  and 600  $\text{g/m}^2$ .
5. A structure according to any one of the preceding claims, wherein the first layer has at least one even surface.
- 20 6. A structure according to any one of the preceding claims, wherein said structure further comprises a wire net which is fixed to the first layer or to the second layer.
7. A structure according to any one of claims 1 to 5, wherein said structure is sandwiched between a first wire net (14) and a second wire net (15), said first net (14) being located at the inlet side, said second wire net (15) being located at the outlet side, said first wire net having meshes which are smaller than the second wire net and having wires with a diameter which is thicker than the diameter of the wires in the second wire mesh.
- 25 8. A structure according to claim 7, wherein said first wire net (14) is a calandered wire net.
9. A structure according to any one of the preceding claims, wherein said first layer is obtainable by means of a cold isostatic pressing operation.
- 30 10. A method of manufacturing a layered filtering structure (10), said method comprising the following steps:
  - 35 (a) sintering a web of metal fibers to form a first layer (12);
  - (b) compacting said first layer (12) to a porosity below 55 %;
  - (c) providing a web of metal fibers to form a second layer (13);
  - (d) bringing said first compacted layer (12) and said second layer (13) in contact with each other to form a layered assembly;
  - 40 (e) sintering said layered assembly to form a coherent entity wherein said second layer has a porosity which is at least 20 % higher than the porosity of the first layer.
11. A method according to claim 10 wherein said compacting is done by means of a cold isostatic pressing operation.
- 45





European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 99 20 0036

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	DATABASE WPI Section Ch, Week 8949 Derwent Publications Ltd., London, GB; Class J01, AN 89-360955 XP002104572 & JP 01 270918 A (FUKUI SHINTA KK) , 30 October 1989 * abstract *	1	B01D39/20
A	EP 0 561 001 A (NIPPON SEISEN CO., LTD.) 22 September 1993 * claims *	1-3, 10	
A	WO 94 14608 A (BEKAERT) 7 July 1994		
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			B01D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 2 June 1999	Examiner Plaka, T
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO Form 1503 03/82 (P4C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 20 0036

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02-06-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 561001 A	22-09-1993	DE 69217039 D	06-03-1997
		DE 69217039 T	07-05-1997
		US 5492623 A	20-02-1996
		WO 9306912 A	15-04-1993
		JP 2857494 B	17-02-1999
WO 9414608 A	07-07-1994	BE 1006452 A	30-08-1994
		AT 141080 T	15-08-1996
		AU 674369 B	19-12-1996
		AU 5555994 A	19-07-1994
		CA 2151477 A	07-07-1994
		CN 1089548 A, B	20-07-1994
		DE 69303932 D	12-09-1996
		DE 69303932 T	30-01-1997
		EP 0674582 A	04-10-1995
		ES 2092883 T	01-12-1996
		JP 8504692 T	21-05-1996
		US 5679441 A	21-10-1997

EPO FORM P0489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82